Claybrook.

FORMELLA

Prepare to be wowed by this beautifully tactile series of largely recycled tiles, created without the use of a kiln. Raw materials from quarries in Italy are mixed as a powder alongside pigments and cement. The tiles are suitable for use on either walls or floors.

8 COLOURS / 2 MOSAICS / 1 FINISH / 2 FORMATS



Formella samples



Formella samples

COLOURS



Natural




Stone



Salmon




Clay



Sage



Apple



Fern




Plum

MOSAICS



Mosaic Clay Mix



Mosaic Sage Mix

FORMAT	SIZE (mm)	THICKNESS (mm)	FINISH	COLOURS	RECOMMENDED GROUT WIDTH (mm)	BOX QTY
Rectangle	54 x 165	15	Composite Stone	All	3	54
Mosaic	123 x 250	15	Composite Stone	All	3	16

Shade Variation / V3 - Moderate

Slip Rating / R11 A+B+C * | PTV 36+ Shod

Recycled Content / 60%

Material / Composite Stone

Requires Sealing / Yes

If you require any further assistance regarding specification data, technical advice or samples, please contact enquiries@claybrookstudio.co.uk or technical@claybrookstudio.co.uk

111124

Claybrook.

FORMELLA

Installation and Technical Advice

Planning & Layout - All substrates should be flat, movement-free, dust-free and primed using Ardex P51 Primer and Bonding Agent. We do not recommend Formella tiles for wet-room floors, however they can be used on shower walls if the substrate is suitably tanked and any movement is made absolutely minimal. We do not recommend fixing any tile directly to standard plasterboard and/or walls that have been skimmed with a thin coat of plaster. We recommend the use of tile backer board and/or a membrane system in any wet areas.

Cutting Advice – We recommend using a flat-bed water-cooled tile cutter and planning the tile layout in such a way to avoid cuts less than 15mm. Always cut through the tile with the visible face uppermost and tidy any chipping with a rubbing/sanding stone or wet and dry paper. Ensure the tile cutter blade is sharp, clean, unslotted and continuous with a smooth cutting face. Also ensure the water is regularly changed otherwise excess staining can occur.

Sealing & Grouting Advice – For full details on sealing and grouting, please ask your installer to read the Formella Installation Guide.

Ongoing Maintenance – We recommend using EcoProTec Stone and Porcelain Aftercare Cleaner for daily cleaning purposes, as this will not attack the surface of the tile or grout. For an occasional deep clean, you can use EcoProTec Intensive Cleaner at the dilution advice on the bottle although you will need to apply the Ceramatt to reseal. Please read the Formella Installation Guide for further information.

If you require any further assistance regarding specification data, technical advice or samples, please contact enquiries@claybrookstudio.co.uk.

TECHNICAL DATA	INDUSTRY STANDARD	REQUIREMENT	PRODUCT VALUE
Impact Resistance	BS UNI EN 14617		Breaking energy (J) = 2,94
Fire Resistance	D.M. 10/03/2005 anx C		A1 without obbligation of proof
Chemical Resistance (domestic)	UNI EN 14617-10:2012	UB min	C4

If you require any further assistance regarding specification data, technical advice or samples, please contact enquiries@claybrookstudio.co.uk or technical@claybrookstudio.co.uk