Claybrook.

HOXTON SQUARE

Gorgeous longer style porcelain tiles in three shade options, each replicating the tones and texture of natural bricks. The design takes its cues from the industrial spaces of Hoxton in East London. Suitable for both wall or floor.

3 COLOURS / 1 FINISH / 1 FORMAT



Hoxton Square Jopling



Hoxton Square Emin

COLOURS



Emin



Hirst



Jopling

FORMAT	SIZE (mm)	THICKNESS (mm)	FINISH	COLOURS	RECOMMENDED GROUT WIDTH (mm)	BOX QTY
Brick	48 x 450	10	Porcelain	All	3	32

* A ramp slip rating (R) and/or PTV Slider 96/55 value where quoted, are determined from tests carried out on one batch and the result can vary from batch to batch. Please contact technical@claybrookstudio.co.uk for further information.

11.25

Claybrook.

HOXTON SQUARE

Installation and Technical Advice



Shade Variation / V4 - Extreme



Slip Rating / R11 * / A+B+C



Material / Porcelain



Requires Sealing / No

Recycled Content / 20%

Planning & Layout - All substrates should be flat, sound and dust free. All wet areas need to be suitably tanked and if the tiles are being fixed to stud walls or joist floors, then all movement must be made absolutely minimal using suitable plywood or tile backer board. Avoid brick-bonding the Allaperto 120x60 with a 1/2 overlap, instead opt for a 1/3 overlap to avoid any lipping.

Cutting Advice – Always use a water-cooled tile cutter and plan the tile layout to avoid cuts of less than 15mm where possible. Always cut through the tile with the visible face uppermost and tidy any slight chipping with a rubbing/sanding stone. Ensure the blade is kept clean with a keen, sharp cutting edge, otherwise excess chipping will occur.

Sealing & Grouting Advice - No sealer required. To avoid excessive grout residue, we recommend using our Ardex FL format grout which has been tested with our products and is available to purchase online. We do not recommend using contrasting-coloured or fine grouts for joint widths down to 1mm, as these can cling to the surface making the tiles more difficult to clean-down after grouting.

Ongoing Maintenance – We recommend using EcoProtec's Stone and Porcelain Aftercare Cleaner for daily cleaning purposes, as this will not affect the tile's slip rating and will not attack the surface of the grout. For an occasional dee per clean, you can use EcoProtec's Stone and Tile Intensive Cleaner. The tile does not need re-sealing.

Installation Notes: During the laying operations for optimal mixing, we recommend taking the pieces from multiple boxes.

TECHNICAL DATA	INDUSTRY STANDARD	REQUIREMENT	PRODUCT VALUE
Surface Appearance (% of surface free of flaws)		≥95%	>95%
Water Absorption	BS UNI ENISO 10545-3	≤0.5%	<0.5%
Breaking Strength	BS UNI ENISO 10545-4	≥35N/mm2	≥35N/mm2
Resistance to Abrasion	BS UNI ENISO 10545-7	PEI	PEI IV
Thermal Shock Resistance	BS UNI ENISO 10545-9	Pass	Pass
Frost Resistance	BS UNI ENISO 10545-12	No alteration to surface	No alteration
Chemical Resistance (domestic)	BS UNI ENISO 10545-13	UB min	Conforms
Stain Resistance (domestic)	BS UNI ENISO 10545-14	Declared value	Class 4

If you require any further assistance regarding specification data, technical advice or samples, please contact enquiries@claybrookstudio.co.uk or technical@claybrookstudio.co.uk