Claybrook.

TOTANA

This Spanish porcelain series cleverly replicates natural travertine stone, with a distinctive and decorative appearance in a neutral sandy shade. The Totana collection is available in a series of medium and larger sizes and has both vein cut and cross cut options.

1 COLOUR / 2 FINISHES / 3 FORMATS

Totana

Totana

COLOURS

Totana

VEIN CUT

Totana Vein Cut

FORMAT	SIZE (mm)	THICKNESS (mm)	FINISH	COLOURS	RECOMMENDED GROUT WIDTH (mm)	BOX QTY
Rectangle Vein Cut	1200 x 600	11	Porcelain	All	3	2
Square	600 x 600	10	Porcelain	All	3	3
Square	800 x 800	10	Porcelain	All	3	2

Print colours may vary from actual product, so tile samples should be requested before ordering.
For advice on shade variation of V3 and above, please speak to our showroom.

* A ramp slip rating (R) and/or PTV Slider 96/55 value where quoted, are determined from tests carried out on one batch and the result can vary from batch to batch. Please contact technical@claybrookstudio.co.uk for further information.

Claybrook.

TOTANA

Installation and Technical Advice

Shade Variation / Vein Cut V3 - Moderate
Cross Cut V2 - Slight

Material / Porcelain

Slip Rating / R10 | PTV 36+ Shod

Requires Sealing / No

Recycled Content / 36%

Planning & Layout - All substrates should be flat, sound and dust free. All wet areas need to be suitably tanked and if the tiles are being fixed to stud walls or joist floors, then all movement must be made absolutely minimal using suitable plywood or cement board. Avoid brick-bonding the Totana 120x60 with a 1/2 overlap, instead opt for a 1/3 overlap to avoid any lipping. This is a porcelain tile designed to replicate travertine stone, therefore notable colour, shade and surface variation should be expected within and between production batches.

Cutting Advice – Always use a water-cooled tile cutter and plan the tile layout to avoid cuts of less than 15mm where possible. Always cut through the tile with the visible face uppermost and tidy any slight chipping with a rubbing/sanding stone. Ensure the blade is kept clean with a keen, sharp cutting edge, otherwise excess chipping will occur.

Sealing & Grouting Advice - No sealer required. To avoid excessive grout residue, we recommend using our Ardex FL format grout which has been tested with our products and is available to purchase online. We do not recommend using contrasting-coloured or fine grouts for joint widths down to 1mm, as these can cling to the surface making the tiles more difficult to clean-down after grouting. The intentionally distressed edge may result in a larger grout joint if not cleaned back correctly.

Ongoing Maintenance – We recommend using EcoProtec's Stone and Porcelain Aftercare Cleaner for daily cleaning purposes, as this will not affect the tile's slip rating and will not attack the surface of the grout. For an occasional dee per clean, you can use EcoProtec's Stone and Tile Intensive Cleaner. The tile does not need re-sealing.

For further advice on installation please contact **technical@claybrookstudio.co.uk** with any questions.

TECHNICAL DATA	INDUSTRY STANDARD	PRODUCT VALUE (R10)	PRODUCT VALUE (R11)
Length and Width	BS UNI ENISO 10545-2	>0.6%	>0.6%
Thickness	BS UNI ENISO 10545-2	≤5%	≤5%
Edge Straightness	BS UNI ENISO 10545-2	>0.5%	>0.5%
Rectangularity	BS UNI ENISO 10545-2	>0.5%	>0.5%
Surface Flatness	BS UNI ENISO 10545-2	>0.5%	>0.5%
Surface Appearance (% of surface free of flaws)		>95%	>95%
Water Absorption	BS UNI ENISO 10545-3	>0.08%	>0.08%
Breaking Strength	BS UNI ENISO 10545-4	≥50N/mm2	≥52N/mm2
Resistance to Abrasion	BS UNI ENISO 10545-7	>140mm3	>140mm3
Thermal Shock Resistance	BS UNI ENISO 10545-9	Pass	Pass
Frost Resistance	BS UNI ENISO 10545-12	No alteration	No alteration
Chemical Resistance (domestic)	BS UNI ENISO 10545-13	UA, ULA, UHA	UA, ULA, UHA
Stain Resistance (domestic)	BS UNI ENISO 10545-14	Class 5	Class 4

If you require any further assistance regarding specification data, technical advice or samples, please contact enquiries@claybrookstudio.co.uk or technical@claybrookstudio.co.uk